

Material - ASTM B 462 N06200

Standard Specification for Forged or Rolled Alloy Pipe Flanges, Forged Fittings, and Valves and Parts for Corrosive High-Temperature Service

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 462 N06200 Forged or Rolled Alloy Pipe Flanges, Forged Fittings, and Valves and Parts for Corrosive High-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe Flanges, Forged Fittings and Valve

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.500 max.		
Copper	Cu %	0.300 - 1.900		
Sulphur	S %	0.010 max.		
Chromium	Cr %	22.000 - 24.000		
Phosphorus	P %	0.025 max.		
Molybdenum	Mo %	15.000 - 17.000	Mechanical Properties Tensile Strength in Mpa 690 min. Yield Strength in Mpa 310 min. Elongation in % 45 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Cobalt	Co %	2.000 max.		
Iron	Fe %	3.000 max.		
Aluminium	Al %	0.500 max.		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06200	ASTM	USA	Forging
B 574 N06200	ASTM	USA	Rod
B 575 N06200	ASTM	USA	Plate, Sheet and Strip
B 619 N06200	ASTM	USA	Pipe
B 622 N06200	ASTM	USA	Pipe and Tube
B 626 N06200	ASTM	USA	Tube
B 472 N06200	ASTM	USA	Billets and Bars

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.