

Material - ASTM B 472 N06030

Standard Specification for Nickel Alloy Billets and Bars for Reforging

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 472 N06030 Nickel Alloy Billets and Bars for Reforging

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Billet and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.500 max.		
Chromium	Cr %	28.000 - 31.500		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	4.000 - 6.000		
Phosphorus	P %	0.040 max.		
Nb + Ta	Nb% + Ta%	0.300 - 1.500	Mechanical Properties Tensile Strength in Mpa 586 min. Yield Strength in Mpa 241 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Tungsten	W %	1.500 - 4.000		
Copper	Cu %	1.000 - 2.400		
Cobalt	Co %	5.000 max.		
Iron	Fe %	13.000 - 17.000		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 581 N06030	ASTM	USA	Rod
B 582 N06030	ASTM	USA	Plate, Sheet and Strip
B 462 N06030	ASTM	USA	Pipe Flanges, Forged Fittings and Valve
B 619 N06030	ASTM	USA	Pipe
B 622 N06030	ASTM	USA	Pipe and Tube
B 626 N06030	ASTM	USA	Tube
SB-581 N06030	ASME	USA	Rod

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.