

Material - ASTM B 516 N06600

Standard Specification for Nickel-Chromium-Iron Alloy Tubes

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 516 N06600 Nickel-Chromium-Iron Alloy Tubes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	14.000 - 17.000		
Iron	Fe %	6.000 - 10.000		
Nickel	Ni %	72.000 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06600	ASTM	USA	Forging
B 366 N06600	ASTM	USA	Forging
B 517 N06600	ASTM	USA	Pipe
B 564 N06600	ASTM	USA	Forging
B 751 N06600	ASTM	USA	Pipe
B 775 N06600	ASTM	USA	Pipe
B 829 N06600	ASTM	USA	Pipe

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.