

Material - ASTM B 516 N06693

Standard Specification for Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Seamless Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 516 N06693 Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Seamless Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	27.000 - 31.000		
Iron	Fe %	2.500 - 6.000		
Aluminium	Al %	2.500 - 4.000		
Titanium	Ti %	1.000 max.		
Niobium	Nb %	0.500 - 2.500		
Nickel	Ni %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 690 min. Yield Strength in Mpa 345 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 166 N06693	ASTM	USA	Rod, Bar and Wire
B 167 N06693	ASTM	USA	Pipe and Tube
B 168 N06693	ASTM	USA	Plate, Sheet and Strip
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.