

Material - ASTM B 536 N08330

Standard Specification for Nickel-Iron-Chromium-Silicon Alloys Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 536 N08330 Nickel-Iron-Chromium-Silicon Alloys Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.750 - 1.500		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	17.000 - 20.000		
Sulphur	S %	0.030 max.		
Copper	Cu %	1.000 max.		
Phosphorus	P %	0.030 max.		
Nickel	Ni %	34.000 - 37.000	Mechanical Properties Tensile Strength in Mpa 483 min. Yield Strength in Mpa 207 min. Elongation in % 30 min. Reduction of Area in % - Hardness in HRC 70 - 90 Impact in Joule -	
Lead	Pb %	0.005 max.		
Tin	Sn %	0.025 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 511 N08330	ASTM	USA	Bar and Shape
B 512 N08330	ASTM	USA	Billets and Bar
B 535 N08330	ASTM	USA	Pipe and Tube
B 710 N08330	ASTM	USA	Pipe
B 739 N08330	ASTM	USA	Tube
SB-511 N08330	ASME	USA	Bar and Shape
SB-535 N08330	ASME	USA	Pipe and Tube

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.