

Material - ASTM B 564 N06603

Standard Specification for Nickel Alloy Forgings

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 564 N06603 Nickel Alloy Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.400	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.150 max.		
Chromium	Cr %	24.000 - 26.000		
Sulphur	S %	0.010 max.		
Copper	Cu %	0.500 max.		
Aluminium	Al %	2.400 - 3.000		
Titanium	Ti %	0.010 - 0.250		
Phosphorus	P %	0.020 max.		
Iron	Fe %	8.000 - 11.000	Mechanical Properties	
Zirconium	Zr %	0.010 - 0.100	Tensile Strength in Mpa	650 min.
Yttrium	Y %	0.010 - 0.150	Yield Strength in Mpa	300 min.
Nickel	Ni %	Balance	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N06603	ASTM	USA	Tube
N06603	UNS	USA	Tube
B 166 N06603	ASTM	USA	Rod, Bar and Wire
B 167 N06603	ASTM	USA	Pipe and Tube
B 168 N06603	ASTM	USA	Plate, Sheet and Strip
B 516 N06603	ASTM	USA	Tube
B 517 N06603	ASTM	USA	Pipe

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.