

Material - ASTM B 574 N06686 Grade 1

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum Alloy Rod

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 574 N06686 Grade 1 Low-Carbon Nickel-Chromium-Molybdenum Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.750 max.		
Chromium	Cr %	19.000 - 23.000		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	15.000 - 17.000		
Phosphorus	P %	0.040 max.		
Tungsten	W %	3.000 - 4.400		
Iron	Fe %	5.000 max.		
Titanium	Ti %	0.020 - 0.250		
Nickel	Ni %	Balance	Mechanical Properties Tensile Strength in Mpa 690 min. Yield Strength in Mpa 310 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N06686	ASTM	USA	Tube
B 462 N06686	ASTM	USA	Pipe and Valve
B 564 N06686	ASTM	USA	Forging
B 575 N06686	ASTM	USA	Plate, Sheet and Strip
B 619 N06686	ASTM	USA	Pipe
B 622 N06686	ASTM	USA	Pipe and Tube
B 626 N06686	ASTM	USA	Tube

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.