

Material - ASTM B 581 N06007

Standard Specification for Nickel-Chromium-Iron-Molybdenum-Copper Alloy Rod

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 581 N06007 Nickel-Chromium-Iron-Molybdenum-Copper Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 - 2.000		
Chromium	Cr %	21.000 - 23.500		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	5.500 - 7.500		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	2.500 max.		
Iron	Fe %	18.000 - 21.000	Mechanical Properties	
Copper	Cu %	1.500 - 2.500	Tensile Strength in Mpa	586 min.
Tungsten	W %	1.000 max.	Yield Strength in Mpa	207 min.
Nitrogen	N %	0.150 - 0.250	Elongation in %	30 min.
Nb + Ta	Nb% + Ta%	1.750 - 2.500	Reduction of Area in %	-
Nickel	Ni %	Balance	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SB-581 N06007	ASME	USA	Rod
B 582 N06007	ASTM	USA	Plate, Sheet and Strip
B 619 N06007	ASTM	USA	Pipe
B 622 N06007	ASTM	USA	Pipe and Tube
B 626 N06007	ASTM	USA	Tube
SB-619 N06007	ASME	USA	Pipe
SB-626 N06007	ASME	USA	Tube

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.