

Material - ASTM B 582 N06030

Standard Specification for Nickel-Chromium-Iron-Molybdenum-Copper Alloy Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 582 N06030 Nickel-Chromium-Iron-Molybdenum-Copper Alloy Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.500 max.		
Chromium	Cr %	28.000 - 31.500		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	4.000 - 6.000		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	5.000 max.		
Copper	Cu %	1.000 - 2.400	Mechanical Properties	
Tungsten	W %	1.500 - 4.000	Tensile Strength in Mpa	586 min.
Nb + Ta	Nb% + Ta%	0.300 - 1.500	Yield Strength in Mpa	241 min.
Iron	Fe %	13.000 - 17.000	Elongation in %	30 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 581 N06030	ASTM	USA	Rod
B 462 N06030	ASTM	USA	Pipe Flanges, Forged Fittings and Valve
B 619 N06030	ASTM	USA	Pipe
B 622 N06030	ASTM	USA	Pipe and Tube
B 626 N06030	ASTM	USA	Tube
B 472 N06030	ASTM	USA	Billets and Bars
SB-581 N06030	ASME	USA	Rod

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.