

Material - ASTM B 626 N06230

Standard Specification for Nickel and Nickel-Cobalt Alloy Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 626 N06230 Nickel and Nickel-Cobalt Alloy Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.250 - 0.750		
Manganese	Mn %	0.300 - 1.000		
Chromium	Cr %	20.000 - 24.000		
Sulphur	S %	0.015 max.		
Molybdenum	Mo %	1.000 - 3.000		
Phosphorus	P %	0.030 max.		
Boron	B %	0.015 max.		
Lanthanum	La %	0.005 - 0.050	Mechanical Properties	
Iron	Fe %	3.000 max.	Tensile Strength in Mpa	760 min.
Aluminium	Al %	0.500 max.	Yield Strength in Mpa	310 min.
Tungsten	W %	13.000 - 15.000	Elongation in %	40 min.
Cobalt	Co %	5.000 max.	Reduction of Area in %	-
Nickel	Ni %	Balance	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 619 N06230	ASTM	USA	Pipe
B 622 N06230	ASTM	USA	Pipe and Tube
B 435 N06230	ASTM	USA	Sheet, Strip and Plate
B 472 N06230	ASTM	USA	Billets and Bars for Reforging
SB-435 N06230	ASME	USA	Plate, Sheet and Strip
SB-564 N06230	ASME	USA	Forging
SB-572 N06230	ASME	USA	Sheet, Strip and Plate

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.