

Material - ASTM B 673 N08925

Standard Specification for Nickel-Iron-Chromium-Molybdenum and Iron-Nickel-Chromium-Molybdenum-Copper Pipe

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 673 N08925 Nickel-Iron-Chromium-Molybdenum and Iron-Nickel-Chromium-Molybdenum-Copper Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	19.000 - 21.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	6.000 - 7.000		
Phosphorus	P %	0.045 max.		
Copper	Cu %	0.800 - 1.500	Mechanical Properties Tensile Strength in Mpa 600 min. Yield Strength in Mpa 300 min. Elongation in % 40 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Nitrogen	N %	0.100 - 0.200		
Nickel	Ni %	24.000 - 26.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 649 N08925	ASTM	USA	Bar and Wire
A 182 F1925	ASTM	USA	Pipe Flanges, Forged Fittings and Valve
B 625 N08925	ASTM	USA	Plate, Sheet and Strip
B 674 N08925	ASTM	USA	Tube
B 677 N08925	ASTM	USA	Pipe and Tube
SB-625 N08925	ASME	USA	Plate, Sheet and Strip
SB-649 N08925	ASME	USA	Bar and Wire

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.