

Material - ASTM B 688 N08367

Standard Specification for Chromium-Nickel-Molybdenum-Iron Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 688 N08367 Chromium-Nickel-Molybdenum-Iron Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	20.000 - 22.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	6.000 - 7.000		
Phosphorus	P %	0.040 max.		
Nickel	Ni %	23.500 - 25.500		
Nitrogen	N %	0.180 - 0.250	Mechanical Properties	
Copper	Cu %	0.750 max.	Tensile Strength in Mpa	655 min.
Iron	Fe %	Balance	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	100 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N08367	ASTM	USA	Forging
B 691 N08367	ASTM	USA	Rod, Bar and Wire
B 462 N08367	ASTM	USA	Pipe Flanges, Forged Fittings, and Valve
A 314 N08367	ASTM	USA	Bar and Forging
B 472 N08367	ASTM	USA	Billet and Bar
B 690 N08367	ASTM	USA	Pipe and Tube
B 834 N08367	ASTM	USA	Pipe Flanges, Forged Fittings, and Valve

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.