

Material - ASTM B 757 N06110

Standard Specification for Nickel-Chromium-Molybdenum-Tungsten-Alloys Pipe

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 757 N06110 Nickel-Chromium-Molybdenum-Tungsten-Alloys Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	28.000 - 33.000		
Sulphur	S %	0.015 max.		
Molybdenum	Mo %	9.000 - 12.000		
Phosphorus	P %	0.015 max.		
Copper	Cu %	0.500 max.		
Niobium	Nb %	1.000 max.	Mechanical Properties	
Tungsten	W %	1.000 - 4.000	Tensile Strength in Mpa	655 min.
Iron	Fe %	1.000 max.	Yield Strength in Mpa	310 min.
Aluminium	Al %	1.000 max.	Elongation in %	60 min.
Titanium	Ti %	1.000 max.	Reduction of Area in %	-
Nickel	Ni %	51.000 min.	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06110	ASTM	USA	Forging
B 755 N06110	ASTM	USA	Plate, Sheet and Strip
B 756 N06110	ASTM	USA	Rod and Bar
B 758 N06110	ASTM	USA	Tube
B 759 N06110	ASTM	USA	Pipe and Tube
SB-564 N06110	ASME	USA	Forging
N06110	UNS	USA	Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.