

Material - ASTM B 814 N06920

Standard Specification for Nickel-Chromium-Iron-Molybdenum-Tungsten Alloy Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 814 N06920 Nickel-Chromium-Iron-Molybdenum-Tungsten Alloy Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	20.500 - 23.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	8.000 - 10.000		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	5.000 max.	Mechanical Properties Tensile Strength in Mpa 655 min. Yield Strength in Mpa 240 min. Elongation in % 35 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Iron	Fe %	17.000 - 20.000		
Tungsten	W %	1.000 - 3.000		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N06920	UNS	USA	Plate, Sheet and Strip
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.