

Material - ASTM B124 C63200

Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.700 - 9.500	As Drawn or Hardening and Tempering	
Iron	Fe %	3.500 - 4.300		
Manganese	Mn %	1.200 - 2.000		
Ni + Co	Ni% + Co%	4.000 - 4.800		
Lead	Pb %	0.020 max.		
Silicon	Si %	0.100 max.		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 620 min. Yield Strength in Mpa 275 min. Elongation in % 15 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C63200	UNS	USA	Rod, Bar, Tube and Shapes
B150 C63200	ASTM	USA	Rod, Bar and Shape
B283 C63200	ASTM	USA	Forging
SB-150 C63200	ASME	USA	Rod, Bar and Shape
SB-171 C63200	ASME	USA	Plate and Sheet
SB-283 C63200	ASME	USA	Forging
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.