

Material - ASTM B124 UNS C71520

Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B124 Copper and Copper Alloy Forging Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Lead	Pb %	0.020 max.	Normalizing or Annealing or Tempering	
Iron	Fe %	0.400 - 1.000		
Ni + Cu	Ni% + Cu%	29.000 - 33.000		
Manganese	Mn %	1.000 max.		
Sulphur	S %	0.020 max.		
Phosphorus	P %	0.020 max.		
Zinc	Zn %	0.500 max.		
Copper	Cu %	65.000 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	344 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B151 C71520	ASTM	USA	Rod and Bar
B171 C71520	ASTM	USA	Plate and Sheet
B283 C71520	ASTM	USA	Forging
B466 C71520	ASTM	USA	Pipe and Tube
SB-151 C71520	ASME	USA	Rod and Bar
SB-171 C71520	ASME	USA	Plate and Sheet
SB-283 C71520	ASME	USA	Forging

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.