

Material - ASTM B138 C67600

Standard Specification for Manganese Bronze Rod, Bar and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B138 Manganese Bronze Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Iron	Fe %	0.400 - 1.300	Normalizing or Annealing or Tempering	
Manganese	Mn %	0.050 - 0.500		
Lead	Pb %	0.500 - 1.000		
Tin	Sn %	0.500 - 1.500		
Copper	Cu %	57.000 - 60.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 380 - 550 Yield Strength in Mpa 150 - 385 Elongation in % 8 - 20 Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B124 C67600	ASTM	USA	Rod, Bar and Shapes
B283 C67600	ASTM	USA	Forging
SB-283 C67600	ASME	USA	Forging
C67600	UNS	USA	Rod, Bar and Shape
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.