

Material - ASTM B148 Aluminum Bronze UNS C95200

Standard Specification for Alumium - Bronze Sand Castings

Group - Non-Ferrous Alumium Alloy

Sub Group - ASTM B148 Alumium - Bronze Sand Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Iron	Fe %	2.500 - 4.000	As-Cast	
Aluminium	Al %	8.500 - 9.500		
Copper	Cu %	86.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 450 min. Yield Strength in Mpa 170 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN 110 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B271 C95200	ASTM	USA	Casting
B148 Grade A	ASTM	USA	Casting
SB-148 C95200	ASME	USA	Casting
SB-148 Grade A	ASME	USA	Casting
C95200	SAE	USA	Casting
CA952	SAE	USA	Casting
CACIn701	KS	Korea	Ingot and Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.