

Material - ASTM B148 C95500

Standard Specification for Aluminum-Bronze Sand Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B148 Aluminum-Bronze Sand Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	10.000 - 11.500	As-Cast or Solution Annealing or Annealing	
Iron	Fe %	3.000 - 5.000		
Manganese	Mn %	3.500 max.		
Ni + Co	Ni% + Co%	3.000 - 5.500		
Copper	Cu %	78.000 min.		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 620 - 760 Yield Strength in Mpa 275 - 415 Elongation in % 5 - 6 Reduction of Area in % - Hardness in HB 190 - 200 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C95500	UNS	USA	Rod, Bar, Tube and Shapes
B30 C95500	ASTM	USA	Ingot and Casting
B271 C95500	ASTM	USA	Casting
SB-148 C95500	ASME	USA	Casting
SB-505 C95500	ASME	USA	Casting
CA955	SAE	USA	Casting
C95500	SAE	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.