

ASTM B148 Manganese - Nickle Aluminum Bronze UNS C95700

Standard Specification for Alumium - Bronze Sand Castings

Group - Non-Ferrous Alumium Alloy

Sub Group - ASTM B148 Alumium - Bronze Sand Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Lead	Pb %	0.030 max.	As-Cast	
Silicon	Si %	0.100 max.		
Ni + Cu	Ni% + Cu%	1.500 - 3.000		
Manganese	Mn %	11.000 - 14.000		
Iron	Fe %	2.000 - 4.000		
Aluminium	Al %	7.000 - 8.500		
Copper	Cu %	71.000 min.		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	620 min.
			Yield Strength in Mpa	275 min.
			Elongation in %	20 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B505 C95700	ASTM	USA	Casting
B148 Grade F	ASTM	USA	Casting
B30 9F	ASTM	USA	Casting
SB-148 C95700	ASME	USA	Casting
SB-148 Grade 9F	ASME	USA	Casting
SB-148 Grade F	ASME	USA	Casting
CACIn704	KS	Korea	Ingot and Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.