

Material - ASTM B150 UNS C61400

Standard Specification for Aluminum Bronze Rod, Bar and Shapes

Group - Non-Ferrous Aluminum Alloy

Sub Group - ASTM B150 Aluminum Bronze Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Phosphorus	P %	0.015 max.	As Drawn or Stress Relieving	
Lead	Pb %	0.010 max.		
Zinc	Zn %	0.200 max.		
Manganese	Mn %	1.000 max.		
Iron	Fe %	1.500 - 3.500		
Aluminium	Al %	6.000 - 8.000		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 485 min. Yield Strength in Mpa 205 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B100 C61400	ASTM	USA	Plate and Sheet
B111 C61400	ASTM	USA	Tubes
B169 C61400	ASTM	USA	Sheet, Strip and Bar
B171 C61400	ASTM	USA	Plate and Sheet
B315 C61400	ASTM	USA	Pipe and Tube
CA614	SAE	USA	Casting
SB-150 C61400	ASME	USA	Rod, Bar and Shapes

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.