

Material - ASTM B150 UNS C64210

Standard Specification for Aluminium Bronze Rod, Bar and Shapes

Group - Non-Ferrous Aluminium Alloy

Sub Group - ASTM B150 Aluminium Bronze Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Arsenic	As %	0.150 max.	As Drawn or Stress Relieving or Hot Rolled	
Lead	Pb %	0.050 max.		
Zinc	Zn %	0.500 max.		
Tin	Sn %	0.200 max.		
Silicon	Si %	1.500 - 2.000		
Manganese	Mn %	0.100 max.		
Ni + Cu	Ni% + Cu%	0.250 max.		
Iron	Fe %	0.300 max.		
Aluminium	Al %	6.300 - 7.000		
Copper	Cu %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	65 - 95
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C64210	ASTM	USA	Rod, Bar and Shape
B150 C64210	ASTM	USA	Rod, Bar and Shape
B283 C64210	ASTM	USA	Forging
SB-150 C64210	ASME	USA	Rod, Bar and Shape
SB-283 C64210	ASME	USA	Forging
C64210	UNS	USA	Casting
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.