

Material - ASTM B151 C70620

Standard Specification for Copper-Nickel-Zinc Alloy and Copper-Nickel Rod and Bar

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B151 Copper-Nickel-Zinc Alloy and Copper-Nickel Rod and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	Normalizing or Annealing or Tempering	
Iron	Fe %	1.000 - 1.800		
Manganese	Mn %	1.000 max.		
Ni + Co	Ni% + Co%	9.000 - 11.000		
Phosphorus	P %	0.020 max.		
Lead	Pb %	0.020 max.		
Sulphur	S %	0.020 max.		
Zinc	Zn %	0.500 max.		
Cu + Ag	Cu% + Ag%	86.500 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	260 - 415
-	-	-	Yield Strength in Mpa	105 - 260
-	-	-	Elongation in %	10 - 30
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B124 C70620	ASTM	USA	Rod, Bar and Shapes
B171 C70620	ASTM	USA	Plate and Sheet
B283 C70620	ASTM	USA	Forging
B466 C70620	ASTM	USA	Pipe and Tube
SB-151 C70620	ASME	USA	Rod and Bar
SB-171 C70620	ASME	USA	Plate and Sheet
SB-283 C70620	ASME	USA	Forging

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.