

Material - ASTM B151 C77000

Standard Specification for Copper-Nickel-Zinc Alloy (Nickel Silver) and Copper-Nickel Rod and Bar

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B151/B151M Copper-Nickel-Zinc Alloy (Nickel Silver) and Copper-Nickel Rod and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod and Bar

Chemical Composition			Heat Treatment	
Iron	Fe %	0.250 max.	Normalizing or Annealing or Tempering	
Manganese	Mn %	0.500 max.		
Ni + Co	Ni% + Co%	16.500 - 19.500		
Lead	Pb %	0.050 max.		
Cu + Ag	Cu% + Ag%	53.500 - 56.500		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 485 - 760 Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuNi18Zn27	IS	India	Rod and Bar
CuNi18Zn27	ISO	International	Plate, Sheet and Strip
B122 C77000	ASTM	USA	Plate, Sheet, Strip and Rolled Bar
B206 C77000	ASTM	USA	Wire
CuNi18Zn20	ISO	International	Plate, Sheet and Strip
CuNi18Zn27	AFNOR NF	France	Plate, Sheet and Strip
CuNi18Zn27	DIN	Germany	Plate, Sheet and Strip

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.