

Material - ASTM B176 C85800

Standard Specification for Copper Alloys Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B176 Copper Alloys Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.550 max.	As-Cast	
Arsenic	As %	0.050 max.		
Iron	Fe %	0.500 max.		
Manganese	Mn %	0.250 max.		
Ni + Co	Ni% + Co%	0.500 max.		
Phosphorus	P %	0.010 max.		
Lead	Pb %	1.500 max.		
Sulphur	S %	0.050 max.		
Antimony	Sb %	0.050 max.		
Silicon	Si %	0.250 max.	Mechanical Properties	
Tin	Sn %	1.500 max.	Tensile Strength in Mpa	379 min.
Zinc	Zn %	31.000 - 41.000	Yield Strength in Mpa	207 min.
Copper	Cu %	57.000 min.	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C85800	UNS	USA	Rod, Bar, Tube and Shapes
B30 C85800	ASTM	USA	Casting
CA858	SAE	USA	Casting
C85800	SAE	USA	Casting
C85800	UNS	USA	Casting
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.