

Material - ASTM B176 C99700

Standard Specification for Copper Alloy Die Castings

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B176 Copper Alloy Die Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.500 - 3.000	As-Cast	
Iron	Fe %	1.000 max.		
Manganese	Mn %	11.000 - 15.000		
Nickel	Ni %	4.000 - 6.000		
Lead	Pb %	2.000 max.		
Tin	Sn %	1.000 min.		
Zinc	Zn %	19.000 - 25.000		
Copper	Cu %	54.000 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C99700	UNS	USA	Rod, Bar, Tube and Shapes
B30 C99700	ASTM	USA	Ingot and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.