

Material - ASTM B224 C14700

Standard Specification for Copper and Copper-Alloy

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B224 Copper and Copper-Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Phosphorus	P %	0.002 - 0.005	Normalizing or Annealing or Tempering	
Sulphur	S %	0.200 - 0.500		
Copper	Cu %	99.90 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Tensile Strength in Mpa	154.500 - 698.200
-	-	-	Yield Strength in Mpa	55 - 367
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C14700	UNS	USA	Rod, Bar, Tube and Shapes
B283 C14700	ASTM	USA	Forging
B301 C14700	ASTM	USA	Rod, Bar, Wire and Shapes
SB-283 C14700	ASME	USA	Forging
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.