

Material - ASTM B271 C92300

Standard Specification for Copper-Base Alloy Centrifugal Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B271 Copper-Base Alloy Centrifugal Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.250 max.		
Ni + Cu	Ni% + Cu%	1.000 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	0.300 - 1.000		
Silicon	Si %	0.005 max.		
Tin	Sn %	7.500 - 9.000		
Zinc	Zn %	2.500 - 5.000		
Copper	Cu %	85.000 - 89.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	248 min.
-	-	-	Yield Strength in Mpa	110 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C92300	UNS	USA	Rod, Bar, Tube and Shapes
B30 2B	ASTM	USA	Ingot and Casting
B30 C92300	ASTM	USA	Casting
B505 C92300	ASTM	USA	Casting
B584 C92300	ASTM	USA	Casting
SB-505 C92300	ASME	USA	Casting
CA923	SAE	USA	Ingot and Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.