

Material - ASTM B271 Leaded Yellow Brass UNS C85400

Standard Specification for Copper-Base Alloy Centrifugal Castings

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B271 Copper-Base Alloy Centrifugal Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	0.500 - 1.500	As-Cast	
Lead	Pb %	1.500 - 3.800		
Zinc	Zn %	24.000 - 32.000		
Iron	Fe %	0.700 max.		
Ni + Co	Ni% + Co%	1.000 max.		
Aluminium	Al %	0.350 max.		
Silicon	Si %	0.050 max.		
Copper	Cu %	65.000 - 70.000	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	207 min.
			Yield Strength in Mpa	76 min.
			Elongation in %	20 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 C85400	ASTM	USA	Ingot and Casting
B271 C85400	ASTM	USA	Casting
B584 C85400	ASTM	USA	Casting
C85400	SAE	USA	Casting
CA854	SAE	USA	Casting
C85400	AS	Australia	Casting
CACIn202	KS	Korea	Ingot and Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.