

Material - ASTM B271 Nickel Alumium Bronze UNS C95520

Standard Specification for Copper-Base Alloy Centrifugal Castings

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B271 Copper-Base Alloy Centrifugal Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	0.250 max.	As-Cast or Solution Annealing or Annealing or Normalizing	
Lead	Pb %	0.030 max.		
Zinc	Zn %	0.300 max.		
Iron	Fe %	4.000 - 5.500		
Ni + Co	Ni% + Co%	4.200 - 6.000		
Aluminium	Al %	10.500 - 11.500		
Manganese	Mn %	1.500 max.		
Silicon	Si %	0.150 max.		
Copper	Cu %	74.500 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 C95520	ASTM	USA	Ingot and Casting
B271 C95520	ASTM	USA	Casting
B505 C95520	ASTM	USA	Casting
SB-148 C95520	ASME	USA	Casting
78Cu-11Al-5.1Ni-4.8Fe	SAE	USA	Casting
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.