

Material - ASTM B275 S12B

Standard Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

Group - Non-Ferrous Alumium Alloy

Sub Group - ASTM B275 Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	1.000 max.	As-Cast	
Iron	Fe %	2.000 max.		
Magnesium	Mg %	0.100 max.		
Manganese	Mn %	0.350 max.		
Nickel	Ni %	0.500 max.		
Silicon	Si %	11.000 - 13.000		
Tin	Sn %	0.150 max.		
Zinc	Zn %	0.500 max.		
Other	Ot%	0.250 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	295 min.
-	-	-	Yield Strength in Mpa	145 min.
-	-	-	Elongation in %	2.5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
13	AA	USA	Casting
A04130	UNS	USA	Casting
A04130	SAE	USA	Casting
B85 S12B	ASTM	USA	Casting
413.0	NBR	Brazil	Casting
413.0	NMX	Maxico	Casting
413.0	SAE	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.