

Material - ASTM B283 C36500

Standard Specification for Copper and Copper-Alloy Die Forgings

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B283 Copper and Copper-Alloy Die Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Iron	Fe %	0.150 max.	Normalizing or Annealing or Tempering	
Lead	Pb %	0.250 - 0.700		
Tin	Sn %	0.250 max.		
Copper	Cu %	58.000 - 61.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 400 min. Yield Strength in Mpa 160 min. Elongation in % 40 min. Reduction of Area in % - Hardness in HRB 45 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B171 C36500	ASTM	USA	Plate and Sheet
SB-171 C36500	ASME	USA	Plate and Sheet
SB-283 C36500	ASME	USA	Forging
365	AS	Australia	Forging
C36500	AS	Australia	Forging
C36500	UNS	USA	Rod, Bar and Shapes
B124 C36500	ASTM	USA	Rod, Bar and Shapes

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.