

Material - ASTM B30 C94800

Standard Specification for Copper Alloys Ingot and Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B30 Copper Alloys Ingot and Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.200 max.		
Manganese	Mn %	0.200 max.		
Ni + Cu	Ni% + Cu%	4.500 - 6.000		
Phosphorus	P %	0.050 max.		
Lead	Pb %	0.300 - 0.900		
Sulphur	S %	0.050 max.		
Antimony	Sb %	0.100 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	4.700 - 6.000	Mechanical Properties	
Zinc	Zn %	1.300 - 2.500	Tensile Strength in Mpa	276 min.
Copper	Cu %	85.000 - 89.000	Yield Strength in Mpa	138 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C94800	UNS	USA	Rod, Bar, Tube and Shapes
B292-B	ASTM	USA	Casting
B505 C94800	ASTM	USA	Casting
B584 C94800	ASTM	USA	Casting
SB-505 C94800	ASME	USA	Casting
C94800	SAE	USA	Casting
CA948	SAE	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.