

Material - ASTM B369 C96200

Standard Specification for Copper -Nickel Alloy Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B369 Copper -Nickel Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast	
Iron	Fe %	1.000 - 1.800		
Manganese	Mn %	1.500 max.		
Niobium	Nb %	1.000 max.		
Ni + Co	Ni% + Co%	9.000 - 11.000		
Phosphorus	P %	0.020 max.		
Lead	Pb %	0.010 max.		
Sulphur	S %	0.020 max.		
Silicon	Si %	0.500 max.	Mechanical Properties	
Copper	Cu %	Balance	Tensile Strength in Mpa	310 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C96200	UNS	USA	Rod, Bar, Tube and Shapes
B30 C96200	ASTM	USA	Ingot and Casting
C96200	SAE	USA	Casting
CA962	SAE	USA	Casting
SB-369 C96200	ASME	USA	Casting
C96200	AS	Australia	Casting
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.