

Material - ASTM B505 High-Strength Yellow Brass UNS C86200

Standard Specification for Copper Alloy Continuous Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B505 / 505M Copper Alloys for Continuous Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	0.200 max.	As-Cast	
Lead	Pb %	0.200 max.		
Zinc	Zn %	22.000 - 28.000		
Ni + Cu	Ni% + Cu%	1.000 max.		
Iron	Fe %	2.000 - 4.000		
Aluminium	Al %	3.000 - 4.900		
Manganese	Mn %	2.500 - 5.000		
Copper	Cu %	60.000 - 66.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	621 min.
-	-	-	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B147-8B	ASTM	USA	Casting
B271 C86200	ASTM	USA	Casting
CA862	SAE	USA	Casting
SAE 430A	SAE	USA	Casting
SB-505 C86200	ASME	USA	Casting
SB-584 C86200	ASME	USA	Casting
CACIn303	KS	Korea	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.