

Material - ASTM B505 Leaded Naval Brass UNS C85700

Standard Specification for Copper Alloy Continuous Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B505 / 505M Copper Alloys for Continuous Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	0.500 - 1.500	As-Cast	
Lead	Pb %	0.800 - 1.500		
Zinc	Zn %	32.000 - 40.000		
Ni + Cu	Ni% + Cu%	1.000 max.		
Iron	Fe %	0.700 max.		
Aluminium	Al %	0.800 max.		
Silicon	Si %	0.05 max.		
Copper	Cu %	58.000 - 64.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	276 min.
-	-	-	Yield Strength in Mpa	97 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B176 C85700	ASTM	USA	Casting
B271 C85700	ASTM	USA	Casting
B30 C85700	ASTM	USA	Casting
B505 C85700	ASTM	USA	Casting
B584 C85700	ASTM	USA	Casting
SB-584 C85700	ASME	USA	Casting
CACIn203	KS	Korea	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.