

Material - ASTM B505 Lead Tin Bronze UNS C92200

Standard Specification for Copper Alloy Continuous Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B505 / 505M Copper Alloys for Continuous Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	5.500 - 6.500	As-Cast	
Lead	Pb %	1.000 - 2.000		
Zinc	Zn %	3.000 - 5.000		
Ni + Cu	Ni% + Cu%	1.000 max.		
Iron	Fe %	0.250 max.		
Antimony	Sb %	0.250 max.		
Sulphur	S %	0.050 max.		
Phosphorus	P %	1.500 max.		
Aluminium	Al %	0.005 max.		
Silicon	Si %	0.005 max.	Mechanical Properties	
Copper	Cu %	86.000 - 90.000	Tensile Strength in Mpa	262 min.
-	-	-	Yield Strength in Mpa	131 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 C92200	ASTM	USA	Ingot and Casting
B61 C92200	ASTM	USA	Casting
SB-61 C92200	ASME	USA	Casting
SB-505 C922000	ASME	USA	Casting
CA922	SAE	USA	Casting
SAE 622	SAE	USA	Casting
CACIn407	KS	Korea	Ingot and Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.