

Material - ASTM B505 UNS C96400

Standard Specification for Copper Alloy Continuous Castings

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B505 / 505M Copper Alloys for Continuous Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Lead	Pb %	0.010 max.	As-Cast	
Ni + Cu	Ni% + Cu%	28.000 - 32.000		
Iron	Fe %	0.250 - 1.500		
Sulphur	S %	0.020 max.		
Phosphorus	P %	0.020 max.		
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.500 max.		
Copper	Cu %	65.000 - 69.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	448 min.
-	-	-	Yield Strength in Mpa	241 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B30 C96400	ASTM	USA	Ingot and Casting
B369 C96400	ASTM	USA	Casting
B505 C96400	ASTM	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.