

Material - ASTM B85 G8A

Standard Specification for Aluminium Alloys for Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - ASTM B85/B85M Aluminium Alloys for Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.250 max.	As-Cast	
Iron	Fe %	1.800 max.		
Magnesium	Mg %	7.500 - 8.500		
Manganese	Mn %	0.350 max.		
Nickel	Ni %	0.150 max.		
Silicon	Si %	0.350 max.		
Tin	Sn %	0.150 max.		
Zinc	Zn %	0.150 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance	Mechanical Properties Tensile Strength in Mpa 310 min. Yield Strength in Mpa 190 min. Elongation in % 5 min. Reduction of Area in % - Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B275 G8A	ASTM	USA	Casting
218	AA	USA	Casting
B275 518.0	ASTM	USA	Casting
B85 518.0	ASTM	USA	Casting
A05180	UNS	USA	Casting
518.0	SAE	USA	Casting
ADC5	JIS	Japan	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.