

Material - ASTM B86 ZA27

Standard Specification for Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings

Group - Non-Ferrous Zinc Alloy

Sub Group - ASTM B86 Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	25.000 - 28.000	As-Cast or Aging	
Cadmium	Cd %	0.006 max.		
Chromium	Cr %	0.010 max.		
Copper	Cu %	2.000 - 2.500		
Iron	Fe %	0.075 min.		
Magnesium	Mg %	0.010 - 0.020		
Manganese	Mn %	0.010 max.		
Nickel	Ni %	0.010 max.		
Lead	Pb %	0.006 max.		
Tin	Sn %	0.003 max.		
Zinc	Zn %	Balance	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	310 - 441
			Yield Strength in Mpa	257 - 376
			Elongation in %	1 - 11
			Reduction of Area in %	-
			Hardness in HB	94 - 119
			Impact in Joule	12.8 - 58 @RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZA-27	ANSI/AA	USA	Casting
B240 ZA27	ASTM	USA	Ingot and Casting
Z35841	UNS	USA	Casting
ZP2720	ISO	International	Casting
ZP27	ISO	International	Casting
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.