

Material - ASTM B951 AM50A

Standard Specification for Magnesium-Alloy Die Castings

Group - Non-Ferrous Magnesium Alloy

Sub Group - ASTM B951 Magnesium-Alloy Die Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	4.400 - 5.400	As-Cast	
Copper	Cu %	0.010 max.		
Iron	Fe %	0.004 max.		
Manganese	Mn %	0.260 - 0.600		
Nickel	Ni %	0.002 max.		
Other	Ot%	0.020 max.		
Silicon	Si %	0.100 max.		
Zinc	Zn %	0.220 max.		
Magnesium	Mg %	Balance		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	200 min.
			Yield Strength in Mpa	110 min.
			Elongation in %	10 min.
			Reduction of Area in %	-
			Hardness in HB	58 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AM50A	ANSI/AA	USA	Casting
EN-MB21220	ONORM	Australia	Ingot and Casting
EN-MBMgAl5Mn	ONORM	Australia	Ingot and Casting
EN-MB21220	CSN	Czech Republic	Ingot and Casting
EN-MBMgAl5Mn	CSN	Czech Republic	Ingot and Casting
B94 AM50A	ASTM	USA	Casting
B275 AM50A	ASTM	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.