

Material - ASTM B951 M10602

Standard Specification for Codification of Unalloyed Magnesium and Magnesium-Alloys, Cast and Wrought

Group - Non-Ferrous Magnesium Alloy

Sub Group - ASTM B951 Codification of Unalloyed Magnesium and Magnesium-Alloys, Cast and Wrought

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	5.500 - 6.500	As-Cast	
Copper	Cu %	0.010 max.		
Iron	Fe %	0.005 max.		
Manganese	Mn %	0.240 - 0.600		
Nickel	Ni %	0.002 max.		
Other	Ot%	0.020 max.		
Silicon	Si %	0.100 max.		
Zinc	Zn %	0.220 max.		
Magnesium	Mg %	Balance	Mechanical Properties Tensile Strength in Mpa 220 min. Yield Strength in Mpa 130 min. Elongation in % 8 min. Reduction of Area in % - Hardness in HB 62 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AM60B	ANSI/AA	USA	Casting
B94 AM60B	ASTM	USA	Casting
B951 AM60B	ASTM	USA	Casting
B275 AM60B	ASTM	USA	Casting
EN-MB21230	BDS	Bulgaria	Ingot and Casting
EN-MBMgAl6Mn	AFNOR NF	France	Ingot and Casting
EN-MB21230	DIN	Germany	Ingot and Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.