

Material - ASTM B983 N07718

Standard Specification for Precipitation Hardened or Cold Worked, Seamless Nickel Alloy Pipe and Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B983 N07718 Precipitation Hardened or Cold Worked, Seamless Nickel Alloy Pipe and Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.350 max.		
Manganese	Mn %	0.350 max.		
Chromium	Cr %	17.000 - 21.000		
Molybdenum	Mo %	2.800 - 3.300		
Aluminium	Al %	0.200 - 0.800		
Niobium	Nb %	4.750 - 5.500		
Phosphorus	P %	0.015 max.		
Sulphur	S %	0.015 max.	Mechanical Properties	
Boron	B %	0.006 max.	Tensile Strength in Mpa	1034 min.
Cobalt	Co %	1.000 max.	Yield Strength in Mpa	862 min.
Titanium	Ti %	0.650 - 1.150	Elongation in %	20 min.
Nickel	Ni %	50.000 - 55.000	Reduction of Area in %	-
Copper	Cu %	0.300 max.	Hardness in HRC	40 min.
Iron	Fe %	Balance	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel 718	SAE	USA	Tube
N07718	UNS	USA	Tube
WL 2.4668	DIN	Germany	Bars and Wire for Screws and Bolts
B670 N07718	ASTM	USA	Plate, Sheet and Strip
B834 N07718	ASTM	USA	Pipe Flange, Fitting and Valve
B637 N07718	ASTM	USA	Bar and Forging
SB-637 N07718	ASME	USA	Bar and Forging

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.