

Material - ASTM B983 N07740

Standard Specification for Precipitation-Hardening Nickel Alloys Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B983 N07740 Precipitation-Hardening Nickel Alloys Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.005 - 0.080	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	23.500 - 25.500		
Molybdenum	Mo %	2.000 max.		
Cobalt	Co %	15.000 - 22.000		
Aluminium	Al %	0.200 - 2.000		
Nb + Ta	Nb% + Ta%	0.500 - 2.500		
Titanium	Ti %	0.500 - 2.500	Mechanical Properties	
Boron	B %	0.0006 - 0.006	Tensile Strength in Mpa	1035 min.
Copper	Cu %	0.500 max.	Yield Strength in Mpa	620 min.
Iron	Fe %	3.000 max.	Elongation in %	20 min.
Phosphorus	P %	0.030 max.	Reduction of Area in %	-
Sulphur	S %	0.030 max.	Hardness in BHN	-
Nickel	Ni %	Balance	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel Alloy 740H	Gravity	India	Plate, Sheet and Strip
B872 N07740	ASTM	USA	Plate, Sheet and Strip
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.