

Material - ASTM F 2281 601

Standard Specification for Stainless Steel and Nickel Alloy Bolts, Screw and Stud

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM F 2281 601 Stainless Steel and Nickel Alloy Bolts, Screw and Stud

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bolts, Screw and Stud

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	21.000 - 25.000		
Nickel	Ni %	58.000 - 63.000		
Aluminium	Al %	1.000 - 1.700		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	571 min.
-	-	-	Yield Strength in Mpa	172 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	65 - 85
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 166 N06601	ASTM	USA	Rod, Bar and Wire
B 167 N06601	ASTM	USA	Pipe and Tube
B 168 N06601	ASTM	USA	Plate, Sheet and Strip
B 751 N06601	ASTM	USA	Rod, Bar and Wire
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.