

Material - ASTM F 2281 660

Standard Specification for Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM F 2281 660 Seamless Nickel and Nickel Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	13.500 - 16.000		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	1.000 - 1.500		
Aluminium	Al %	0.350 max.		
Boron	B %	0.003 - 0.010	Mechanical Properties Tensile Strength in Mpa 896 min. Yield Strength in Mpa 586 min. Elongation in % 15 min. Reduction of Area in % - Hardness in HRC 22 - 37 Impact in Joule -	
Titanium	Ti %	1.900 - 2.300		
Vanadium	V %	0.100 - 0.500		
Nickel	Ni %	24.000 - 27.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Incoloy A-286	Gravity	India	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire
A 959 Type 660	ASTM	USA	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.