

Material - ASTM F 563 R30563

Standard Specification for Cobalt-20Nickel-20Chromium-3.5Molybdenum- 3.5Tungsten-5Iron Alloy for Surgical Implant Applications

Group - Non-Ferrous Cobalt Alloys

Sub Group - ASTM F 563 R30563 Cobalt-20Nickel-20Chromium-3.5Molybdenum- 3.5Tungsten-5Iron Alloy for Surgical Implant Applications

Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing	
Chromium	Cr %	18.000 - 22.000		
Molybdenum	Mo %	3.000 - 4.000		
Nickel	Ni %	15.000 - 25.000		
Iron	Fe %	4.000 - 6.000		
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Sulphur	S %	0.010 max.		
Tungsten	W %	3.000 - 4.000	Mechanical Properties	
Titanium	Ti %	0.500 - 3.500	Tensile Strength in Mpa	600 min.
Cobalt	Co %	Balance	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
R30563	UNS	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.