

Material - ASTM F 90 R30605

Standard Specification for Cobalt-20 Chromium-15 Tungsten-10 Cobalt Alloy for Surgical Implant Applications

Group - Non-Ferrous Cobalt Alloys

Sub Group - ASTM F 90 R30605 Cobalt-20 Chromium-15 Tungsten-10 Cobalt Alloy for Surgical Implant Applications

Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150	As-Cast or Annealing	
Manganese	Mn %	1.000 - 2.000		
Silicon	Si %	0.400 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	19.000 - 21.000		
Nickel	Ni %	9.000 - 11.000		
Tungsten	W %	14.000 - 16.000		
Iron	Fe %	3.000 max.	Mechanical Properties	
Cobalt	Co %	Balance	Tensile Strength in Mpa	860 min.
-	-	-	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
R30605	UNS	USA	Casting
L-605	SAE	USA	Sheet, Strip, Foil and Plate
F2527 R30605	ASTM	USA	Sheet, Strip, Foil and Plate
5832-4	ISO	International	Casting
5832-5	ISO	International	Casting
7402-3	JIS	Japan	Casting
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.