

## Material - ASTM F467 C67500

### Standard Specification for Nonferrous Nuts for General Use

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM F467 Nonferrous Nuts for General Use

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Nut

| Chemical Composition |      |                 | Heat Treatment                                                                                                                                                                                    |  |
|----------------------|------|-----------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|
| Aluminium            | Al % | 0.250 max.      | Normalizing or Annealing or Tempering                                                                                                                                                             |  |
| Iron                 | Fe % | 0.800 - 2.000   |                                                                                                                                                                                                   |  |
| Manganese            | Mn % | 0.050 - 0.500   |                                                                                                                                                                                                   |  |
| Lead                 | Pb % | 0.200 max.      |                                                                                                                                                                                                   |  |
| Tin                  | Sn % | 0.500 - 1.500   |                                                                                                                                                                                                   |  |
| Copper               | Cu % | 57.000 - 60.000 |                                                                                                                                                                                                   |  |
| Zinc                 | Zn % | Balance         |                                                                                                                                                                                                   |  |
| -                    | -    | -               | <b>Mechanical Properties</b><br>Tensile Strength in Mpa -<br>Yield Strength in Mpa 379.2 - 406.8<br>Elongation in % -<br>Reduction of Area in % -<br>Hardness in HRB 60 min.<br>Impact in Joule - |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |
| -                    | -    | -               |                                                                                                                                                                                                   |  |

| Cross Reference Table |          |         |                                 |
|-----------------------|----------|---------|---------------------------------|
| Material              | Standard | Country | Grade Belong to the Industry    |
| B124 C67500           | ASTM     | USA     | Rod, Bar and Shapes             |
| B138 C67500           | ASTM     | USA     | Rod, Bar and Shape              |
| B283 C67500           | ASTM     | USA     | Forging                         |
| CA675                 | SAE      | USA     | Rod, Bar and Shape              |
| SB-283 C67500         | ASME     | USA     | Forging                         |
| SF-467 C67500         | ASME     | USA     | Nut                             |
| SF-468 C67500         | ASME     | USA     | Bolts, Hex Cap Screws and Studs |

For any further inquiries, please do not hesitate to contact us. You may visit our website at [AMTECH TECHNOCAST PVT. LTD.](http://AMTECH TECHNOCAST PVT. LTD.), call us at [+91 9879817994](tel:+919879817994), or email us at [manish@amtechtechnocast.com](mailto:manish@amtechtechnocast.com)

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.