

Material - ASTM F468 Ni400HF

Standard Specification for Nickel-Copper Alloy, Corrosion Resistant Sheet, Strip and Plate

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM F467 Ni400 Nickel-Copper Alloy, Corrosion Resistant Sheet, Strip and Plate

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Sheet, Strip and Plate

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.000 max.		
Iron	Fe %	2.500 max.		
Sulphur	S %	0.024 max.		
Nickel	Ni %	63.000 - 70.000		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 480 - 825 Yield Strength in Mpa 205 min. Elongation in % 20 min. Reduction of Area in % - Hardness in HRC 60 - 95 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Monel 400	SAE	USA	Sheet, Strip and Plate
F467 Ni400	ASTM	USA	Sheet, Strip and Plate
SF467 Ni400	ASME	USA	Sheet, Strip and Plate
SF-468 Ni400	ASME	USA	Sheet, Strip and Plate
SF-468 Ni400HF	ASME	USA	Sheet, Strip and Plate
NCuR	JIS	Japan	Strip
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.